

BETEK-TECT STONEWOOL TR7.5

DESCRIPTION

Betek-Tect Stonewool TR7.5 Thermal Insulation Plate is an inorganic thermal insulation plate produced by melting down volcanic rocks such as basalt and dolomite in high temperature pots and converting them into fibers.

FEATURES

- Offers **superior thermal insulation** with its **ideal thermal conductivity coefficient** ($\lambda_D = 0.035$ W/mK).
- Provides **perfect sound insulation** with its exclusive fiber structure.
- Used reliably in all facade systems in line with the regulations with its **class A1 reaction to fire**.
- Enables **lighter, easier and faster application** with its low density value and ideal plate dimensions.
- Ensures **high energy saving throughout the building life cycle** with its ideal plate thickness and **mechanical resistance in line with the standards**.
- **Ecological and environmentally-friendly** with its **world-class production technology** and **natural raw material content**. Very low dust during cutting.

- Produced in line with the TS EN 13162 Stonewool Product and TS EN 13500 Stonewool System standards.

STORAGE

Store on pallets at a cool and ventilated environment away from direct sunlight and substances like solvents and thinners. Protect against precipitation.

Warning: Abstain from applying plaster on stonewool plates exposed to precipitation, before they are fully dry.

TECHNICAL SPECIFICATIONS	Description		UNIT	CLASS	STANDARD
Material	Stonewool				TS EN 13162
Material Type	ETICS Stonewool				prEN 17237
Fire Response Class	Declared value			A1	EN 13501-1
Width	600		mm		EN 822
Length	1000		mm		EN 822
Thickness (d)	50-90	100-200	mm	T5	EN 823
Thermal Conductivity Coefficient (λ_D)	0.035		W/mK		EN 12667
Thermal Resistance (R_D)	d / λ_D		m ² K/W		
Tensile Strength Perpendicular to Faces	>7,5		kPa	TR7,5	EN 1607
Compressive Strength at 10% Deformation	30	40	kPa	CS(10)30	EN 826
Length Tolerance	± 2%		mm	L2	EN 822
Width Tolerance	± 1.5%		mm	W2	EN 822
Dimensional Stability	± 1%			DS(t)	EN 1604
Water Vapor Absorption (short term - 24 hours)	<1		kg/m ²	WS	EN 1609
Water Vapor Diffusion Resistance Coefficient	1		μ		EN 12086
Temperature Range	(-50) / 750		°C		