

WATER-BASED EXTERIOR PRODUCT GROUP

NIPPON PAINT AQUATIC SILICONED EXTERIOR PAINT

PRODUCT DESCRIPTION

A next generation, silicone emulsion-based, self-cleaning, matt, photocatalytic, top coat exterior paint.

SPECIFICATIONS

Thanks to the new maze texture of Nippon Paint Aquatic, the moisture on the walls are discharged easily and thus, paint peeling is fully prevented when applied in building material standards. As the silicone binder filler pigment system has been developed for the severest climatic conditions, the paint comes as integrated completely with the surface, lasting for years. The photocatalytic centers created with special pigments that are used oxidize and dissolve the dirt on the surface are oxidized, and thus keep the surface clean. Offers high UV resistance thanks to its silicone-modified binder system. It is easy to apply due to its spreading easily over the surface. Saves both time and labor. Does not splash or drip.

APPLICATION SURFACES

Can be applied on plaster, rough plaster, comb mosaic, concrete, exposed concrete, concrete board, MDF, OSB, and even old painted ready-plaster type surfaces that can still support themselves even though they may have lost their color.

APPLICATION

The surface should be stable, dry, clean, and self-supporting. This paint should not be applied directly on lime surfaces or loose layers. When surface correction and repairs are required, Nippon Paint Exterior Paste must be used in accordance with the product label information. Nippon Paint Silicone Exterior Primer should be applied before applying Nippon Paint Aquatic Grained. After the primer dries, apply Nippon Paint Aquatic with a brush and a roller in minimum two coats or by spraying in one coat. Ensure that the surface temperature is between +5°C and +30°C during application. Observe the setting period (28 days) on concrete, brute concrete, new plastered surfaces, and clean the loose plaster particles with scraper or similar methods. Correct and repair the surface if required. During painting and drying periods, the surface needs to be protected from both rain and frost. Application should not be conducted in windy conditions or under direct sunlight. After the application, all used tools should be cleaned with water. There must be 6 to 8 hours waiting time between the primer and each paint coat.

Prefer shady walls if required to be applied in hot weather conditions above +30°C and abstain from application between 11:00 AM and 04:00 PM.

Our products should be applied on substructure surfaces that are built in line with General Construction Specifications dated 30.06.2007 and with no. 26568.

CAUTION: Salt efflorescence and whitening may occur on the paint surface when the paint is applied before the cement-based materials under the paint are fully dried or after the surface is exposed to weather events such as rain etc. before painting. Therefore, the setting periods of cement-based materials should be considered and the surfaces exposed to dew, frost and rain should be allowed to dry before the application.

Pressure For Airless Spraying: 140 bars

Nozzle Angle: 50°C

Nozzle Size (inch): 0.019"-0.021"

Thinning: 5%

THINNING

Thin by a maximum of 15% using clean water. During high volume exterior painting works, the products should be diluted in the same ratio in order to prevent differences in color tone.

DRYING TIME (at 20°C, 65% RH):

Touch Dry: 1 to 2 hours

Second coat application: 6 to 8 hours

Final Dry: 24 hours

BETEK BOYA VE KİMYA SANAYİ A.Ş.

Zümrütevler Mahallesi Üral Sokak No:38 34852 Maltepe / İSTANBUL

Tel: 0216 571 10 00 Faks: 0216 571 13 15 Mersis No: 0167001238900018 - www.nipponboya.com



CONSUMPTION 6 to 10 m² single coat per liter depending on the type, absorbency and structure of the application surface. Perform a controlled sample run to estimate the precise consumption amount.

STORAGE May be stored for 3 years in its unopened packaging in a cool and dry environment protected against frosting and direct sunlight. Close the lid air-tight immediately after application.

PACKAGE

13.5 L, 7.5 L, 2.5 L, 1.25 L



Conforms to TS 7847



TSE

Conforms to the G communiqué

Gloss: Class G3

Dry Film Thickness: Class E2

Granule Size: Class S1

Water Vapor Transmission Rate: Class V2

Water Transmission Rate: Class W3

Crack Coverage Capacity: Class A0

Carbon Dioxide Permeability: Class C0

Pos. No.

15.540.1304

Rate No.

10.300.1012

This technical sheet is prepared based on laboratory data at normal conditions. Consult technical personnel for details that are not provided hereinabove. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change the information provided hereunder.

Where necessary, please refer to Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.

This product is manufactured by Betek A.Ş. with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002.

BETEK BOYA VE KİMYA SANAYİ A.Ş.

Zümrütevler Mahallesi Üral Sokak No:38 34852 Maltepe / İSTANBUL

Tel: 0216 571 10 00 Faks: 0216 571 13 15 Mersis No: 0167001238900018 - www.nipponboya.com

